

LOBADUR® WS EasyFinish (Cork)

One-component waterborne sealer based on polyurethane-acrylate with excellent resistance.

Very low emission according to Emission Code EC1

Article No:	11517	2004/42/CE
Gloss Level:	satin (ca. 20) semi-gloss (ca. 40*)	EU limit value for this product
Package Size:	Satin 5l - semi-gloss 5l, 10l	(cat. A/i): 140g/l (2007/2010)
Giscode	W3+ – substitute product according to TRGS 617	This product satin contains max 80g/l VOC This product semi-gloss contains max 80g/l VOC
Solids:	32 ± 1%	
Viscosity DIN 4:	23 ± 1s	

Range of Use: Cork floors with normal to heavy wear.
The requirements for sportsfloor according to DIN 18032 meet LOBADUR® WS EasyFinish semi-gloss in combination with LOBA® SportCare.

Information on Use:

- Seal cork only after the glue has sufficiently set. (note manufacturers information)
- Do not put material directly on the floor, use the LOBATool sealing bucket.

Setup recommendations:

Untreated natural cork	Prefinished cork
Cork Floors: Roll three applications of LOBADUR® WS EasyFinish onto surface. After the first application drying over night (reduces risk of granule swelling) Intermediate sanding before the last application	Note information given by the cork supplier. In case of a possible recoating after an intermediate sanding, apply one to two coats of LOBADUR® WS EasyFinish using a roller.

Renovation of/ recoating old coverings

Basic cleaning with LOBA® CareRemover. The use of a single disc grinder and the green and red abrasive pads are necessary. Care product remains must be completely cleaned off; even small remains may cause problems with the adhesion of the finish.

Clean with clear water

Thorough intermediate sanding after drying

Apply one to two coats of LOBADUR® WS EasyFinish using a roller

Covering Tool: LOBATool roller DeLuxe 120 or LOBATool roller Microfaser 100 - 120

Covering Quantity: Each roller application 100 - 120 ml/m² (8 - 10 m²/l), 10 – 12 ml / square foot

Drying Time: Earliest possible recoating after 4 to 6 hours, can be carefully walked on after 4 to 6 hours, light wear after 24 hours, reaches final hardness after ca.5 days

Intermediate Sanding: Able to recoat without intermediate sanding within the first 24 hours. After this time an intermediate sanding is necessary. An intermediate sanding before the last application will achieve an even surface.

Thinner: The finish is ready-to-use and cannot be diluted! In case of unfavourable conditions the drying can be delayed by adding a max. of 5% LOBADUR® WS Argo.

Storage and Transportation: +5°C bis +25°C (41°F to 77°F), storable for 12 months, not a hazardous material according to ADR



The general Information on the Use of LOBADUR® WS Products are part of this Information and must be noticed.

LOBA GmbH & Co. KG
Tel: +49 (0) 7156 357 169
Fax: + 49 (0) 7156 357 211
Mail: service@loba.de

* The gloss level is measured at 60°.
It depends on the thickness and the climatic conditions (temp, rel. Air humidity) during drying. The data is not binding